



**GENUINE GEOWEB®
GW30V6 – Wall Sections**

GEOWEB® SYSTEM PERFORMANCE & MATERIAL SPECIFICATION SUMMARY

Property	Value		Test Method			
Base Material	Material Composition	Polymer – Polyethylene with density of 0.935 – 0.965 g/cm ³ (58.4 - 60.2 lb/ft ³)				
	Color	Black - from Carbon Black	Tan, Green, Other Colors with no heavy metal content			
	Stabilizer	Carbon black content 1.5% - 2% by weight	Hindered amine light stabilizer (HALS) 2.0% by weight of carrier			
	Minimum ESCR	5000 hr				
Strip Properties	Sheet Thickness	Prior to Texture: 1.27 mm -5% +10% (50 mil -5% +10%) After Texture: 1.52 mm -5% +10% (60 mil -5% +10%)				
	Surface Treatment	Performance: The polyethylene strips shall be textured and interior strips shall be perforated such that the peak friction angle between the surface of the textured / perforated plastic and a #40 silica sand at 100% relative density shall be no less than 85% of the peak friction angle of the silica sand in isolation when tested by the direct shear method per ASTM D 5321. The quantity of perforations in the interior cells shall remove 16.8% ±1.0% of the cell wall area.	Material: The polyethylene strips shall be textured with a multitude of rhomboidal (diamond shape) indentations. The rhomboidal indentations shall have a surface density of 22 – 31 per cm ² (140 – 200 per in ²). In addition, interior strips shall be perforated with horizontal rows of 10 mm (0.4 in) diameter holes. Perforations within each row shall be 19 mm (0.75 in) on-center. Horizontal rows shall be staggered and separated 12 mm (0.50 in) relative to the hole centers. The edge of strip to the nearest edge of perforation shall be 8 mm (0.3 in) minimum and the centerline of the weld to the nearest edge of perforation shall be 18 mm (0.7 in) minimum. A slot with a dimension of 10 mm x 35 mm (3/8 in x 1 3/8 in) is standard in the center of the non-perforated areas and at the center of each weld.			
Cell & Seam Properties	Cell Details	Depth	Dimensions	Density per m² (yd²)	Area	
	GW30V	150 mm (6 in)	Length 267 mm (10.5 in)	Width 330 mm (13.0 in)	22.7 (16.5)	440 cm ² (68.3 in ²)
	Short-term Seam Peel Strength	Cell Depth 150 mm (6 in)		Minimum Certified Cell Seam Strength 2130 N (480 lbf)		
	Long-term Seam Peel Strength	Long-term seam peel-strength test shall be performed on all resin or pre-manufactured sheet or strips. A 100 mm (4.0 in) wide seam sample shall support a 72.5 kg (160 lb) load for a period of 168 hours (7 days) minimum in a temperature-controlled environment undergoing a temperature change on a 1-hour cycle from ambient room to 54°C (130°F). Ambient room temperature is per ASTM E 41.				
Section Properties	Section Dimension	Section Width	Section Lengths (Cells Long: 3, 4, 5, 6, 7)			
	GW30V	2.64 m (8.67 ft)	Fixed	In direction of section expansion From 0.800 m (2.63 ft) to 1.867 m (6.13 ft) in increments of 267 mm (10.5 in)		
Certifications & Warranties	Geoweb® Material	Geoweb® sections are manufactured under a quality management system that is ISO-9001:2008 certified. For additional certification and warranty information, refer to the Presto Geosystems Geoweb® Cellular Confinement Specification .				

© 2016 Presto Products Company. This specification is copyrighted and based on the use of Genuine Geoweb® manufactured by Presto Products Company (Presto Geosystems). Any use of this specification for any product other than that manufactured by Presto Products Company is strictly prohibited.